



Penthor 1064

Oil tempered silicon/chromium/
vanadium + Nickel alloyed valve
spring wire from shaved wire rod

External Standard:

Non existing

Applications:

Especially suitable for coil springs subjected to high dynamic stresses requiring good fatigue resistance (eg. valve springs), as well as for springs which require high tensile strength and excellent relaxation properties at moderately elevated working temperatures (up to approx. 250° C

Range of diameters:

3.00 to 6.60mm Ø

Chemical composition (heat analysis):

C %	Si %	Mn %	P Max %	S Max %	Cu Max %	Cr %	V %	Ni %
0.50-0.70	1.80-2.20	0.30-1.00	0.020	0.020	0.060	0.85-1.05	0.05-0.25	0.20-0.40

Raw material:

Wire rod made of Si-killed steel according to in-house specifications.

The wire rod is shaved to eliminate surface defects such as seams, cracks and decarburization.

Cleanliness acc. to max. t-method:

Number of non-metallic inclusions in the surface area detected on end samples of the wire rod

Size of inclusions	5-10	>10-15	>15 ¹⁾	µm
Max. number/1000mm ²	50	7	0	

¹⁾ As stated by IVSWMA* it is likely to find occasional inclusions in valve spring quality steel of a size large than 15 µm

IVSWMA: International Valve Spring Wire Manufacturers Association

Mechanical Properties: Penthor 1064

Wire diameter	Tolerance	Tensile strength	Minimum reduction area	Minimum number of torsions min.	Permissible depth of surf. defects ¹⁾	Permissible part decarburization depth ¹⁾
mm	mm	MPa	%			
3.00 to 3.20	±0.025	2130 to 2230	40	5	max 0.5 % of wire diameter	
>3.20 to 3.50		2080 to 2180		4		
>3.50 to 4.00		2080 to 2180				
>4.00 to 4.20	2030 to 2130	3				
>4.20 to 4.50	2030 to 2130					
>4.50 to 4.70	2030 to 2130	3				
>4.70 to 5.00	2030 to 2130					
>5.00 to 5.60	±0.03	1980 to 2080	40	3		
>5.60 to 6.00		1980 to 2080				

- Range of tensile strength within one coil max. 50 MPa
- Ovality: Difference between the largest and smallest diameter of a cross section does not exceed 50% of the diameter tolerance.
- Yield point (0.2% limit) at least 90% of the tensile strength
- Modulus of elasticity
E = 206.000 MPa (Standard)
Shear Modulus
G = 79.500 MPa (Standard)
- Torsion tests are carried out according to EN 10218-1
 - End samples

Surface inspection:

Wires with diameters from 2.5 to 6.5 mm are eddy current surface inspected after oil hardening and tempering using a combination of two methods to detect both transverse and longitudinal defects. Testing of wires <2.50 mm can be agreed upon separately.

Defects S 40 µm are recorded and marked.

Heat treatment:

After coiling, the springs should be stress relieved as soon as possible at 380–425 °C, with a holding time of 30 minutes at temperature.

After shot peening, the springs must be stress relieved at approx. 240 °C for 30 minutes.

Shot peening:

The shot size and blast time must be chosen to ensure complete coverage of the inside of the springs.

Particular attention should be paid to the above in case of springs with small index and pitch.

Please inquire for special tolerances, tensiles, sections, etc.